

## WINE & SPIRITS LABEL PAPERS

	UNIT	STD	ETI MATT WS	ETI MATT WS FROZEN MARTELÉ	ETI WINE	ETI WINE MARTELÉ	ETI WINE FROZEN	ETI WINE FROZEN MARTELÉ	ETI WINE IVORY	ETI WINE IVORY SABLE	KAZAN	KAZAN WS
SUBSTANCE*	gsm	ISO 536	90	90	90	90	90	90	90	90	90	90
CALIPER	micron	ISO 534	90	85	115	110	120	110	120	120	130	115
ROUGHNESS BENDTSEN	ml/min	ISO 8791 - 2			500	800	500	800	350	500	700	700
COBB 60 BACK SIDE	gsm	ISO 535	16	0	24	24	0	0	24	24	30	30
DRY TENSILE	kN/m	ISO 1924 1/2	6,7 - 3,4	6,7 - 3,4	6,8 - 3,2	6,8 - 3,2	7 - 3,2	7 - 3,2	7 - 3,5	7 - 3,5	4,8 - 2,8	4,3 - 2,5
WET TENSILE	kN/m	ISO 1924 1/2	1,7 - 1,2	1,7 - 1,2	0,8 - 0,5	0,8 - 0,5	1 - 0,5	1 - 0,5	1 - 0,5	1 - 0,5	\	2,2 - 0,5
DRY OPACITY	%	ISO 2471	94	94	92	90	92	90	92	90	\	\
WET OPACITY	%	ISO 2471	78	94	83	82	92	90	88	86	\	\
ABSOLUTE MOISTURE	%	ISO 287	5	5	5	5	5	5	5	5	5	5
BRIGHTNESS ISO	%	ISO 2470	93	93	105	104	105	105	88	87	\	\
WHITENESS CIE	%	ISO 11475			150	148	150	150	82	82	\	\

\*: the range of substances for all wine papers is 80 - 110 gsm